



Intermediate Chemicals Company Ltd.
(Arabian Zinc Oxide Factory)
Al Jubail – KSA

Zinc Oxide Granular

| Test Parameters | Specifications |
|----------------------------------------|-----------------|
| Zinc Oxide Content as ZnO on dry basis | 99.9 % |
| Appearance & Color | White Granules |
| Lead Content as Pb | 0.003 max. |
| Cadmium Content as Cd | 0.0005% max. |
| Copper Content as Cu | Nil |
| Iron Content as Fe | 0.001% max. |
| Arsenic Content as As | Nil |
| Sulphur Content as Sulfide | 0.005% max. |
| Loss at 110 C, 1 Hr | 0.15% max. |
| Screen Test | |
| +10 mesh | 5.0 % max. |
| -100 mesh | 15.0 % max. |
| Bulk Density-Tapped | 1.5 – 1.8 gm/cc |

**These are the General Specifications. However, material as per customer's requirement could be offered.*

Applications: ✓ Granular Zinc Oxide is used in such application where properties such as free flow, low dusting and low bulk are required, in the following industries. It is used in Rubber, Paints, Ceramic, Glass

Packing: ✓ Big Bag of 500 / 1000 Kg
✓ 25 Kg PP bags with PE liners

Disclaimer:

“Intermediate Chemicals Co. Ltd. provides the information contained herein in good faith but makes no representation as to its comprehensiveness for a particular purpose. Final determination of suitability of this material is the sole responsibility of the user. Intermediate Chemicals Co. Ltd assumes no liability for reliance upon this information.”